

TOUCH MOREMATT G | COMPACT THE DESIGN MATERIAL PROPERTIES DATA SHEET

MOREMATT G | COMPACT is a non-porous homogeneous high-density material produced by simultaneous application of heat and pressure. The core is composed of paper impregnated with aminoplastic thermosetting resins. The decorative surface is made of impregnated paper coated with special acrylic resins cured trough an electron beam process.

PROPERTIES	TEST METHOD	PROPERTY OR ATTRIBUTE	VALUES	UNIT
GENERAL PROPERTIES				
Surface quality	EN 438-2:2016 Par. 4	Spots, dirt and similar surface defects	≤ 1	mm²/m²
		Fibers, hair and scratches	≤ 10	mm/m²
Dimensional tolerances	EN 438-2:2016 Par. 5	Thickness ⁽¹⁾	$ \begin{array}{lll} \pm \ 0.20 & 2.0 \leq t < 3.0 \\ \pm \ 0.30 & 3.0 \leq t < 5.0 \\ \pm \ 0.40 & 5.0 \leq t < 8.0 \\ \pm \ 0.50 & 8.0 \leq t < 12.0 \\ \pm \ 0.60 & 12.0 \leq t < 16.0 \end{array} $	mm
	EN 438-2:2016 Par. 6	Length and width	+ 10 / - 0	mm
	EN 438-2:2016 Par. 7	Straightness of edges	≤ 1,5	mm/m
	EN 438-2:2016 Par. 8	Squareness	≤ 1,5	mm/m
	EN 438-2:2016 Par. 9	Flatness (measured on full-size sheet)	$\leq 8,0$ 2,0 \leq t < 6,0 \leq 5,0 6,0 \leq t < 10,0 \leq 3,0 t \geq 10,0	mm/m
PHYSICAL PROPERTIES				
Resistance to immersion in boiling water	EN 438-2:2016 Par. 12	Mass increase	≤ 2	%
		Thickness increase	≤ 2	%
	E11 400 2.2010 Tul. 12	Surface appearance	≥ 4	Rating
		Edge appearance	≥ 4	Rating
Dimensional stability at elevated temperatures	EN 438-2:2016 Par. 17	Cumulative dimensional change	≤ 0,4 2,0 ≤ t < 5,0 ≤ 0,3 t ≥ 5,0	Longitudinal % (2)
			≤ 0.8 $2.0 \leq t < 5.0$ ≤ 0.6 $t \geq 5.0$	Transversal % ⁽²⁾
Resistance to impact by large diameter ball	EN 438-2:2016 Par. 21	Drop height Indent diameter	≥ 1400 2,0 ≤ t < 6,0 ≥ 1800 t ≥ 6,0 ≤ 10	mm
Resistance to crazing	EN 438-2:2016 Par. 24	Appearance	≥ 4	Rating
Density	EN ISO 1183	Density	≥ 1,35	g/cm ³
Flexural modulus	EN ISO 178	Stress	≥ 9000	MPa
Flexural strength	EN ISO 178	Stress	≥ 80	Мра
SURFACE PROPERTIES	E14150 170	Jiless	2.00	Ivipa
Resistance to surface wear	EN 438-2:2016 Par. 10	Initial point	≥ 100	Revolutions
Resistance to water vapour	EN 438-2:2016 Par. 14	Appearance	5	Rating
Resistance to dry heat (160°C)	EN 438-2:2016 Par. 16	Appearance	5	Rating
Resistance to wet heat (100°C)	EN 438-2:2016 Par. 18	Appearance	5	Rating
Resistance to scratching	EN 438-2:2016 Par. 25	Force	≥ 4	Rating
Resistance to staining	EN 438-2:2016 Par. 26	Appearance	5 groups 1 & 2 ≥ 4 group 3	Rating
Light Fastness (Xenon-arc)	EN 438 -2:2016 Par. 27	Contrast	≥ 4	Grey scale rating
Surface specular reflectance	ISO 2813	Surface specular reflectance	6 ÷ 15 measured at 85°	Gloss unit
FOOD & HYGIENE PROPERTIES		<u> </u>		
Contact with food - overall migration	Contact with food - overall migration	Contact with food - overall migration	Contact with food - overall migration	Contact with food - overall migration
Evaluation of micro-organisms action	JIS Z 2801:2012	Antimicrobial activity after 24h	> 3 > 99,9	Bacterial viability: Log reduction % Reduction



TOUCH MOREMATT G | COMPACT THE DESIGN MATERIAL PROPERTIES DATA SHEET

ENVIRONMENTAL PROPERTIES						
Formaldehyde emission	EN 13986	Formaldehyde emission rating	E1	Rating		
Volatile organic chemical emission	AFNOR NF EN ISO 16000-9	Classification	A+	Rating		
		TVOC emission	≤ 0,2	mg/m³		
Phenol Free ⁽³⁾	AFNOR NF EN ISO 16000-9	Phenol emission	< 0,002	mg/m³		

Notes

- (1) t: nominal thickness [mm]
- (2) Longitudinal: parallel to the fiber direction. Transversal: at right angles to the fiber direction
- (3) Phenol is not used as raw material in MOREMATT G production. 0,002 mg/m³ is the detection limit (DL) value of the test.

Note to MOREMATT G sheets with adhesive protective film

The protective films are designed for temporary surface protection against dirt, scratches and tool marks; they are not designed for protection against corrosion, humidity or chemicals. The laminates covered with the protective film shall be stored in a clean, dry place (40 to 60 RH%) at room temperature (20 to 25 °C), avoiding weathering and UV exposure. In any case, the removal must be made within four months from the date of shipment by Puricelli. Puricelli cannot be responsible for the misuse of the laminates covered with the protective film, nor for the consequences for non-recommended applications.